

CCIS-1201C

Non-Woven Geotextile

CCIS-1201C is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. CCIS-1201C resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13. CCIS-1201C is NTPEP certified and meets requirements as per AASHTO Standards and/or D.O.T. Standards.

CCIS-1201C conforms to the Minimum Average Roll Values (MARV) listed below:

Property	Method	English (MARV2)	Metric (MARV2)
Grab Tensile Strength	ASTM D 4632	300 lbs.	1.334 kN
Grab Elongation	ASTM D 4632	50%	50%
Trapezoid Tear Strength	ASTM D 4533	115 lbs.	0.511 kN
CBR Puncture Resistance	ASTM D 6241	850 lbs	3.780 kN
Permittivity ⁴	ASTM D 4491	1.0 sec-1	1.0 sec-1
Water Flow ⁴	ASTM D 4491	75 gpm/ft ²	3055 l/min/m ²
Apparent Opening Size (AOS) ^{3&4}	ASTM D 4751	100 Std. U.S. Sieve	0.150 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.

Packaging		
Roll Dimensions (W x L)	12.5 x 360 ft. 15 x 300 ft.	3.81 m x 109.8 m 4.6 m x 91.4 m
Area Per Roll	500 sq. yards	418.3 sq. meters
Estimated Roll Weight	320 lbs.	170 kg

NOTES

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. Maximum Average Roll Value (MaxARV)
4. At time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Cross Country assumes no liability in connection with the use of this information.

**For Pricing And Availability Contact Our
Canadian Sales Team at 780-962-6559 or Visit CrossCountryIS.com**