



CCIS-16ozEnv NON-WOVEN GEOTEXTILE

CCIS-16ozEnv is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. CCIS-16ozEnv resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13.

CCIS-16ozEnv conforms to the Minimum Average Roll Values (MARV) listed below:

PROPERTY	TEST METHOD	ENGLISH (MARV2)	METRIC (MARV2)
Weight	ASTM D 5261	16 oz/yd ²	542 g/m ²
Grab Tensile Strength	ASTM D 4632	425 lbs	1.89 kN
Grab Elongation	ASTM D 4632	50%	50%
Trapezoid Tear Strength	ASTM D 4533	150 lbs	0.667 kN
CBR Puncture Resistance	ASTM D 6241	1200 lbs	5.34 kN
Permittivity ⁴	ASTM D 4491	0.57 sec ⁻¹	0.57 sec ⁻¹
Water Flow ⁴	ASTM D 4491	45 gpm/ft ²	1833 l/min/m ²
Apparent Opening Size (AOS) ^{3&4}	ASTM D 4751	100 US Sieve	0.15 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.

PACKAGING

Roll Dimensions (W x L)	15 ft. x 300 ft.	4.58 m x 91.44 m
Area Per Roll	500 Yd ²	418.06 m ²

NOTES

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. Maximum Average Roll Value (MaxARV)
4. At time of manufacturing. Handling may change these properties.

**For Pricing And Availability Contact
Our Sales Team at 780-962-6559**

